



TRUBUILD STAIN FREE TILE GROUT

Trubuild Stain Free Tile Grout is a three component prepacked epoxy grout which is specially designed • Remove dust, oil, debris and sealer from the joints for grouting of ceramic tiles, vitrified tiles and stone where staining is expected. It provides a stain free, chemical resistant, hard wearing tile joints. Meets the requirement of EN 13888 & ISO 13007.

APPLICATIONS

- It is hygienic, hard wearing stain free water miscible epoxy resin tile grout for areas like:
- Bathrooms, fountains and swimming pools
- Kitchens, cafeterias, restrooms, schools
- Factories, Workshops and ware-houses
- Pharma industry, hospitals & labs
- Commercial & residential buildings

ADVANTAGE

- It is stain free & easily cleaned
- It is easy to install and clean
- It resists bacterial growth
- It is resistant to mild chemicals & acids
- It is non-cracking or powdering
- It is water cleanable when fresh
- Available in range of attractive colors

HOW TO USE

- with the help of wire brush or air blower.
- Take Part-A & Part-B into a suitable container and mix perfectly with a trowel or a slow drill mixer.
- Now add Part-C powder in this mix slowly to get a uniform consistency. Mix as stiff as possible to work into the joints.
- Using a hard rubber grout float, compact the grout into the joints ensuring that they are completely filled.
- Within 30 minutes of application, clean off surplus grout. Use an emulsifying pad & gripper dampened with clean water to break down (emulsify) the grout residue.
- Do not allow water to flow/run into ungrouted joints.

RESTRICTIONS ON USE

- This should not be used when temperature is below 5°C and falling.
- This should not be exposed to moving water during TRIBUTOR application.





TECHNICAL INFORMATION

STANDARD	RESULTS		
	Low Viscous Liquid		
	Semi Transparent		
	Milky White		
ASTM D-2196-10	2000-3000 Cps		
ASTM D1652-11	180-200 Eq/gm		
	Low Viscous Liquid		
	Transparent		
	Light Brown		
ASTM D-2196-10	1000- 2000 Cps		
IS 9162-1979	380-420 Mg KOH/gm		
	100:40 By Weight		
ASTM D2471-99	450-500 Minutes At 25°C of 100g Mix		
	12 to 15 Hours At 25°C		
	24 Hours At 25°C		
	>5°C		
	ASTM D-2196-10 ASTM D1652-11 ASTM D-2196-10 IS 9162-1979		



COVERAGE (APPROXIMATE SQ.FT COVERAGE PER 5 KG UNIT)									
SIZE OF	WIDTH OF JOINT								
THETILE	2mm	3mm	4mm	6mm	8mm	10mm	12mm		
100 X 100 X 3 mm	264	177	133	90	68	55	46		
150 X 150 X 4 mm	298	196	149	100	75	61	51		
200 X 150 X 5 mm	269	181	136	91	69	55	46		
150 X 300 X 6 mm	263	175	132	88	66	53	44		
300 X 300 X 6mm	394	263	198	132	100	80	67		
450 X 300 X 7mm	405	270	202	135	101	81	68		
600 X 450 X 6mm	506	337	253	169	127	101	85		
600 X 600 X 8mm	291	394	295	197	148	119	99		
600 X 900 X 11mm	515	343	258	171	129	103	86		
900 X 900 X 12 mm	590	393	295	197	148	118	99		

SHELF-LIFE

24 months in unopened packaging in a strictly dry and cool storage place.

PACKING

1kg, 5 kg



