

### Product Description :

**MYMIX - GTA** (Glass Tile Adhesive) is a polymer modified, multi-purpose thin-set adhesive for fixing glass mosaic, glass brick wall, swimming pool tiles, marble and natural stones on variety of interior and exterior substrates for wall and floor applications

### Application :

- Specially for internal & external floors and walls
- All types of tiles and stones

**FOR BETTER APPLICATION  
USE A NOTCH TROWEL OF  
APPROPRIATE NOTCH SIZE**

### Advantages :

- Multipurpose hi-polymer modified thin set adhesive
- High bond strength suitable for exterior application of various tiles & stones
- High flexible adhesive
- Non-skid adhesive
- Water resistance properties
- Better open time with good workability

### Suitable Substrates :

- Concrete
- Cement plaster
- Cement mortar beds
- Brick masonry
- Ceramic tile & stone
- Cement terrazzo
- Concrete masonry
- Gypsum wall board (interior application)

### How to apply :

- Add 25 kg of "MYMIX - GTA" (Glass Tile Adhesive) to approx. 6.5 to 7.5 litres of cool and clean tap water and stir properly for 5 minutes by hand or an electric stirrer to get a smooth and homogeneous mixture

- After stirring; wait for 10 minutes, stir once again and apply the adhesive on the sub-floor with 2 mm adhesive notch trowel for glass mosaic
- Press the tiles within 15 to 20 minutes with a shuffling movement into the adhesive. Check properly to ensure that the back of the tile is in full contact with the adhesive
- Remove excess adhesive immediately from the joints
- The proper preparation of the surface will make the fixing easier and quicker ensuring a better finish.
- New concrete is recommended to be 1 month old for every 25 mm thickness and completely dried before tiling
- Under normal circumstances, i.e. a temperature of 20°C and a relative humidity of 65%, the joints may be filled after minimum 24 hours

### Technical Details : (As per IS 15477 & ANSI 118.4)

Sr. No.	Testing Parameter	Specification
1	GTA - Mixing Ratio	6.5 to 7.5 litre water for 25 kg material approx 25-30% by weight
2	Product Colour	White and Grey
3	Workability	Easy mixing and self curing
4	Application	Easy notching
5	Open time @ 23-27°C	40 - 45 minutes
6	Pot Life	4 hours
7	Setting time	24 hours
8	Trafficable Time	24 hours
9	Shear Adhesion :	
A	Dry condition after 24 hrs	4.8 KN
B	Dry condition after 14 days	19.50 KN
C	Heat ageing condition	14.00 KN
D	Wet condition	12.50 KN
10	Tensile Adhesion	
A	Dry condition	2200 N
B	Wet condition	2100 N

### Coverage :

- At 3 mm bed thickness 65-75 sq. ft./ per 25 kg bag.

### Storage :

- Store in a cool & dry place. Protect from direct sunlight.

### Colour :

- White and Grey

### Packing Detail :

- Available in 25 kg bag
- Available in 40 kg bag Project pack on demand

### Shelf Life :

- 12 months from the date of manufacturing in unopen condition



Thakurji  
DISTRIBUTORS  
+91 95375 65835